

Sediul: Moinești, str. Albotești, nr.1 bis
Nr. Registrul Comerțului: J 04/442/1995
Cod Fiscal: RO 7258130
Cont BCR Moinești
COD IBAN: RO36RNCB0029 0140 1001 0001

Tel.: 004 0234 361 440 / 441, Fax: 0234 362 640
Mobil: 0740 030951
E-mail: topcomposite@dypety.ro
Internet: www.dypety.ro

TOPREBAR



Bara cu suprafata nervurata si aderenta imbunatatita de diametru 16 mm, din rasina poliesterica si fibra de sticla E
FRP rebar ribbed surface bar with improved adherence, diameter 16 mm in polyester resin reinforced with E-Glass

Diametrul barei – Bar diameter	16 mm
Sectiunea nominala a barei- Nominal section of the bar	201.06 mm ²

CARACTERISTICI FIZICE SI MECANICE- PHYSICAL AND MECHANICAL CHARACTERISTICS

	Unitate de masura-Unit	Valoare-Value
Forța de rupere la traciune - Tensile breaking force	N	191173
Forța de rupere la incovoiere - Bending breaking force	N	2210
Forța de rupere la indoire -Bending breaking force	N	3759
Rezistența la rupere- Breaking strength	Mpa	>936
Modul de elasticitate-Elastic modulus	Gpa	>46
Tip de fibra- Type of fiber		Fibra de sticla E-filament continuu- Continuous E-filament fiberglass
Tip de rasina- Type of resin		Poliesterica- Polyester
Continut de fibra- Fiber content		75%
Continut de rasina- Resin content		25%
Rezistența la coroziune- Corrosion resistance		Non coroziv- Not corrosive
Conductivitate electrica- Electrical conductivity		Dielectric
Proprietati magnetice- Magnetic properties		Neinfluentat de campurile magnetice- Uninfluenced by magnetic fields

AVANTAJE- BENEFITS

Durabila - **Durable**
Rezistente la degradare atmosferica -
Resistance to atmospheric degradation
Rezistența înaltă la medii alcaline- **High resistance to alkaline environments**
Usor de transportat - **Easy to transport**
Rapid și ușor de utiliza- **Quick and easy to use**