

Sediul: Moinești, str. Albotești, nr.1 bis  
 Nr. Registrul Comerțului: J 04/442/1995  
 Cod Fiscal: RO 7258130  
 Cont BCR Moinești  
 COD IBAN: RO36RNCB0029 0140 1001 0001

Tel.: 004 0234 361 440 / 441, Fax: 0234 362 640  
 Mobil: 0740 030951  
 E-mail: topcomposite@dypety.ro  
 Internet: www.dypety.ro

## TOPREBAR



Bara cu suprafata nervurata si aderenta imbunatatita de diametru 6 mm, din rasina poliesterica si fibra de sticla E  
 FRP rebar ribbed surface bar with improved adherence, diameter 6 mm in polyester resin reinforced with E-Glass

Diametrul barei – Bar diameter	6 mm
Sectiunea nominala a barei- Nominal section of the bar	28.27 mm <sup>2</sup>

### CARACTERISTICI FIZICE SI MECANICE- PHYSICAL AND MECHANICAL CHARACTERISTICS

	Unitate de masura-Unit	Valoare-Value
Forta de rupere la tractiune - Tensile breaking force	N	44200
Forta de rupere la incovoiere - Bending breaking force	N	800
Forta de rupere la indoire -Bending breaking force	N	1530
Rezistenta la rupere- Breaking strength	Mpa	>1115
Modul de elasticitate-Elastic modulus	Gpa	>46
Tip de fibra- Type of fiber		Fibra de sticla E-filament continuu- Continuous E-filament fiberglass
Tip de rasina- Type of resin		Poliesterica- Polyester
Continut de fibra- Fiber content		75%
Continut de rasina- Resin content		25%
Rezistenta la coroziune- Corrosion resistance		Non coroziv- Not corrosive
Conductivitate electrica- Electrical conductivity		Dielectric
Proprietati magnetice- Magnetic properties		Neinfluentat de campurile magnetice- <b>Uninfluenced by magnetic fields</b>

### AVANTAJE- BENEFITS

Durabila - **Durable**  
 Rezistente la degradare atmosferica -  
**Resistance to atmospheric degradation**  
 Rezistenta inalta la medii alcaline- **High resistance to alkaline environments**  
 Usor de transportat - **Easy to transport**  
 Rapid si usor de utiliza- **Quick and easy to use**